



TIMNA COPPER MINES Ltd

Head Office: Doar-na Eilot 88000, Israel

Tel: +972-8-6374171/2

Fax: +972-8-6374174

E-mail: timna@timna.co.il

Website: www.timna.co.il

Product Specification

Aluminium Granules

Size Grades

1 – 6 mm

Chemical Analysis (% weight)

Please note that the content of impurities varies in a wide range accordingly to purity degree of raw material we use. The following values are typical, while cleaner product is available on request.

Aluminium + Magnesium	98% min
Magnesium	2.7% max
Copper	0.2% max
Zinc	0.2% max
Lead	0.02% max
Manganese	0.8% max
Iron	1% max
Silicon	0.25% max
Carbon	0.1% max

Apparent Bulk Density

0.9 – 1.2 g/cm³

Appearance

- A. Heavy irregular granules of primary source**
- B. Flat and irregular granules with high specific surface area**

Dotan yosef
Quality Manager, TIMNA COPPER MINES Ltd.



Revision 02, September 2018